



**TOYOBO CO., LTD.** HARDLEN-VYLON International Sales Department

OSAKA 2-8-2, Dojimahama, Kita-ku, Osaka, Japan  
TOKYO 1-17-10, Kyobashi, Chuo-ku, Tokyo, Japan

Tel: +81-6-6348-4448 Fax: +81-6-6348-3752  
Tel: +81-3-6887-8771 Fax: +81-3-6887-8887

February, 2019

## Technical Information

### **HARDLEN<sub>TM</sub> DX-526P**

Adhesion promoter for polyolefin

HARDLEN<sub>TM</sub> DX-526P has an excellent solubility in various solvents, and solution stability is very good at low temperature.

#### **(1) Properties**

Polymer	Chlorinated Polyolefin
Cl %	26
Viscosity (mPa·s) <sup>a</sup>	230

<sup>a</sup> 20wt% Toluene solution at 25°C

#### **(2) Characteristics of HARDLEN<sub>TM</sub> DX-526P**

1. Excellent solubility in various solvents.
2. Solution stability is very good at low temperature.

#### **(3) Product Form / Packing**

Pellet / 20kg NET in paper bag

Note: Data listed are given only for reference and do not represent the guaranteed values.